



Primer 9911

Productsheet

Description

SABA Primer 9911 is a 2-component primer based on epoxy.

Special properties

- Brings about excellent adherence to porous, bituminous substrates in combination with SABA polysulfide sealants

Field of application

SABA Primer 9911 is very well suited for priming bituminous substrates like asphalt.

Method of use

For more information concerning the method of use please read the corresponding SABA Info sheets and/or Primer lists.

Technical data

| | | Part A | Part B |
|------------------------|-----------------|---------------------------------------|--------------------------------|
| Basis | | : epoxide | amine |
| Viscosity at 23 °C | (EN 12092) | : watery | watery |
| Density | (EN ISO 2811-2) | : approx. 950 kg/m ³ | approx. 1125 kg/m ³ |
| Solids content | | : approx. 42% | approx. 100 % |
| Solvents | | : ketones | none |
| Flashpoint | | : approx. 12 °C | |
| Drying time | | : approx. 30 minutes | |
| Open time | | : minimum 30 min. and maximum 6 hours | |
| Potlife after mixing | | : 2 to 3 hours | |
| Coverage | | : approx. 100 g/m ² | |
| Work temperature | | : minimum + 5 °C, maximum + 30 °C | |
| Storage temperature | | : minimum + 5 °C, maximum + 30 °C | |
| Temperature resistance | | : from - 40 °C up to + 120 °C | |
| Shelf life | | : 12 months in unopened packing | |

Order information

| | |
|---------|------------|
| Packing | Tin |
| Content | 0,5 litres |

| | |
|-------------|---------------------|
| Colour | Light yellow |
| Article No. | 100485 |

Safety recommendations

For more information concerning safety please read the corresponding SABA Safety Data Sheet.

SABA Dinxperlo BV

Industriestraat 3, NL-7091 DC Dinxperlo, PO Box 3, NL-7090 AA Dinxperlo, the Netherlands, Tel +31 (0) 315 658999, Fax +31 (0) 315 653207, E-mail info@saba.nl, Internet www.saba.nl.

Our recommendations and instructions for use are based on the present status of know-how and technique. Clients and users should evaluate our products by themselves, with regard to utilization and requirements of their own choice. We shall take no responsibility in case our products are not being used subject to our recommendations and/or instructions for use. Furthermore, General Terms and Conditions of SABA Dinxperlo BV, will apply to our recommendations, instructions for use and the delivery of our products.

Version: 2009-01-08, replaces all previous versions